

40 Sieve Inlet Protection Data Sheet

PRODUCT DATA SHEET

PROPERTY	TEST METHOD	MARV
Tensile Strength (Grab)	ASTM D-4632	370/200
Elongation	ASTM D-4632	15%
Puncture	ASTM D-4833	90 lbs
Mullen Burst	ASTM D-3786	400 psi
Trapezoidal Tear	ASTM D-4533	115 x 75 lbs
UV Resistance	ASTM D-4355	90%
Apparent Opening Size (AOS)	ASTM D-4751	40 US Std. Sieve
Percent Open Area (POA)	CW-02215 Mod.	10%
Permittivity	ASTM D-4491	2.0 sec⁻¹
Water Flow Rate	ASTM D-4491	140 gpm/ft²

The property values listed above are subject to change without notice.