

Sediment Cage™ Geotextile Properties

PROPERTY	TEST METHOD	MARV
Tensile Strength (Grab)	ASTM D-4632	350/250
Elongation	ASTM D-4632	15%
Puncture	ASTM D-4833	120 lbs
Mullen Burst	ASTM D-3786	450 psi
Trapezoidal Tear	ASTM D-4533	140 x 105 lbs
UV Resistance	ASTM D-4355	90%
Apparent Opening Size (AOS)	ASTM D-4751	40 US Std. Sieve
Percent Open Area (POA)	CW-02215 Mod.	6%
Permittivity	ASTM D-4491	.5 sec⁻¹
Water Flow Rate	ASTM D-4491	75 gpm/ft²

The property values listed above are subject to change without notice.